

Amendments to the Specification:

Please replace paragraph [0070] with the following amended paragraph:

[0070] Then, the thermal decomposition temperatures of the polymers (H), (I) and (J) were measured by DSC (differential ~~thermal operation~~ scanning calorimeter). With this, they showed high heat resistances of 465°C, 450°C and 420°C in terms of 5% weight reduction temperature. Furthermore, their dielectric constants at 1MHz were measured by using an LCR meter. With this, they respectively showed low values of 2.8, 2.6 and 2.4.